



Prof. Gary Hamed

“The Discovery of Carbon Black / Natural Rubber Vulcanizates for Automobile and Truck Tires and the Mechanism for the Exceptionally High Tear Strength of these Nanocomposites”

University of Akron
Professor Emeritus

Department of Polymer Science
Host: Dave Dillard



Abstract: Natural rubber vulcanizates containing 0-50 phr of a fine carbon black (N115, $d \approx 27$ nm) were prepared and tensile strengths of normal (no pre-cut) and edge pre-cut specimens were determined. Normal tensile strengths of all vulcanizates were similar. At the relatively slow strain rate experienced wholesale by normal uncut specimens, all vulcanizates, prior to crack initiation, strain-crystallized sufficiently to be strong. However, pre-cut specimens experience increased strain rate at a cut tip. Magnification of the strain rate increases as cut depth c increases. Fracture in the gum NR and vulcanizates with up to 14 phr of black occurred by simple forward crack growth from a cut tip, and all exhibited a critical cut size c_{cr} , where strength dropped abruptly. Furthermore, for these lightly filled samples, strength and c_{cr} **decreased** with increased black content. This indicates less strain-crystallization before rupture of pre-cut specimens when levels of black are low. This effect is attributed to rapid straining at a cut tip and hindering of the chain mobility necessary for crystallization. When black content was increased to 15 phr, with $1 \text{ mm} < c < 2 \text{ mm}$, about 50% of specimens retained simple lateral fracture and were weak, but, the other 50% developed deviated cracks (knotty tearing) and were much stronger. With 50 phr of black, all pre-cut specimens exhibited knotty tearing and were significantly stronger than corresponding pre-cut gum specimens, especially at large c . High strengths with sufficient black levels are attributed to increased strain-crystallization and super-blunting (multiple cracks) at a cut tip. These inhibit forward crack growth. For carbon black to enhance strain-crystallization relative to the gum, it appears there must be enough of it to form a bound rubber/black network. If the black concentration is less than this percolation threshold, strain-crystallization is hindered at a cut tip.

University of Akron
Department of Polymer Science
Akron, OH 44325
Phone: 330-972-6831
E-mail: hamed@uakron.edu

Bio: Professor Hamed has been at The University of Akron for nearly forty years. He has published about 110 papers on adhesion and the mechanical properties of rubber. He has been active in the ACS Rubber Division and received the Sparks-Thomas and Whitby Awards from this organization. He is also a fellow of the Adhesion Society.

Sponsored by the
Solvay International Chemical Group

DATE: APRIL 3, 2019

TIME: 11:15AM-12:15PM

LOCATION: FRALIN AUDITORIUM

